



TECNOLOGÍA DEPORTIVA, S. A. LABORATORIO DE ENSAYOS I+D

Informe de ensayos

Type of test : Test meshes Humidity : 65 %
Operator : Daniel Cantó Temperature : 20 °C
Specifications Requirements : SI Actions :
Date of Test : 02/01/2018


Velocidad de ensayo : 250 mm/min
Standard Test : ISO 1806

Sample Identification : NET 3MM; PAHT; WHITE; MESH 35mm

Test results:

Nr	F _{max} kN	ΔL en F _{max} %	Energía Rotura J
1	1,41	94,9	30,12
2	1,35	95,0	26,69
3	1,49	98,9	30,06

Serial Graphic:



Statistic:

Serie	F _{max} kN	ΔL en F _{max} %	Energía Rotura J
n = 3			
$\bar{x}$	1,42	96,3	28,96
s	0,0723	2,3	1,96
v	5,10	2,37	6,78